



# zandleven coatings

## ZANCOR® LASPRIMER

alkyd

One component fast drying welding and transport primer, free from lead and chrome.

- Manageable within 10 minutes at a surface temperature of 30 °C and a film thickness of 25 µm.
- Excellent welding properties, does not develop any harmful vapours.
- Term of protection about 6 months at a film thickness of 25 µm, depending on the roughness of the surface and atmospheric circumstances.
- After drying recoatable with practically any paint system.

### Product information

Finish	Mat
Colour	Red-brown
Mass density	approx. 1.5 kg/L
Solids content by volume	approx. 53 volume %
VOC	approx. 375 gr./L (volatile organic compound)
Recommended film thickness	As welding primer 25 µm d.f.t. per layer Other applications 25-60 µm d.f.t. per layer 50-115 µm w.f.t. per layer
Theoretical spreading rate	(undiluted) At 25 µm d.f.t. 21.2 m²/L At 60 µm d.f.t. 8.8 m²/L
Practical spreading rate	Depending on several factors like shape of object, profile of surface, method of application, application circumstances and experience. A few guiding principles are: Brush/roller 85-90% of the theoretical spreading rate Spraying 50-70% of the theoretical spreading rate
Flashpoint ISO 1523	Paint 25 °C Thinner FGM 631 26 °C Thinner WTD 107 14 °C
Dry temperature resistance	200 °C
Durability	At least 12 months, provided that it has been stored in closed original packing at a dry and cool spot.

### Drying times

For d.f.t. up to 25 µm

Dust dry

Manageable

Recoatable:

Minimum interval

Maximum interval

Recoatable with two components paint systems

30 °C	20 °C	5-10 °C
6 minutes	10 minutes	15 minutes
8 minutes	12 minutes	20 minutes
2 hours	4 hours	6 hours
Unlimited, provided that the surface is dry and clean.		
Film thickness, ventilation, temperature and relative humidity are of great influence on the drying times.		
After 1 to 4 weeks, depending on the temperature and layer thickness		



## Application instructions

### Application conditions

During application and hardening the temperature should be above 5 °C to obtain optimal qualities.

The surface should remain free from water and ice and the temperature of the surface should at least be 2 °C above dew point.

During application and hardening in closed or small spaces, it is necessary to refresh the air continually to remove the solvent vapours, this because of drying, health and safety.

### Usage information

Type of thinner

Recommended thinner  
(depending on application  
and equipment)

Nozzle orifice

Nozzle pressure

Maximum attainable d.f.t.

Cleaning of tools

Airless-spray	Air spray
FGM 631 / WTD 107	FGM 631 / WTD 107
	10 – 25 vol. %
0.41 – 0.46 mm 0.016 – 0.018 inch	1.0 – 1.5 mm
120 – 150 bar	2 – 3 bar
60 µm	40 µm
Thinner BG 91	

### Surface conditions

Steel

New steel:

Blasting according to the ISO norm 8501-1:1988 Sa 2½.

Roughness profile Ra 10-12 µm Rz 50-60 µm.

Surface must be clean and dry.

Repair and maintenance:

Clean the surface thoroughly with a suitable cleaning preparation or by means of steam cleaning.

Remove salts and other water-soluble impurity by spraying with clean tap-water under high pressure.

Remove rust a.o. by (water)blasting Sa 2½ or derust mechanical until St. 2-3. Apply the advised paint system on a clean and dry surface.

- Mechanical or hand derusting gives less quality than (water)blasting and will result in less protection of the applied paint system.

### Safety description

See safety data sheet

### Ventilation rules

Minimum required quantity of air to comply with:		
	MAC	10 % LEL
Zancor Lasprimer	2245 m³/L	88 m³/L
Thinner FGM 631	3995 m³/L	160 m³/L
Thinner WTD 107	4085 m³/L	168 m³/L

MAC = Maximum Acceptable Concentration

LEL = Lower Explosion Limit

Also consult the security information sheets

### Pretreatment / Labeling / Technical Terms (downloadable from [www.zandleven.com](http://www.zandleven.com))

A 1 Labeling of paint products in the European Community

A 2 Physical data

A 4 General guidelines for steel preservation

A 6 Pretreatment of construction steel

These data have been drawn up to the best of our knowledge and were correct at the date of issue. However we cannot accept full responsibility, because de choice of products and circumstances during elaboration of the systems fall outside our judgement.

This documentation sheet will not automatically be replaced in case of modification.

The English language text is a translation. In case of doubt the Dutch language original text has to be consulted as the authoritative text.