



# zandleven coatings

Corrosie classificatie volgens ISO 12944-5

Beschermingsduur	Systeemnr.	Type	Product	laagdikte	
C3	1	AK	Zancor SF-X	80 µm	
		AK	Zancor ZF-xx	40 µm	
		Totaal	120 µm		
	0 - 5 jaar	2	EP	Monopox Metalcoat ZL 70	80 µm
			PUR	Polyfinish MU-DL	40 µm
			Totaal	120 µm	
	5 - 15 jaar	1	EP	Monopox Metalcoat ZL 70	80 µm
			PUR	Polyfinish HS	80 µm
			Totaal	160 µm	
		2	EP	Monopox Metalcoat ZL 70	100 µm
PUR			Polyfinish HS	60 µm	
Totaal			160 µm		
> 15 jaar	1	EP	Acraton HS-U	120 µm	
		PUR	Polyfinish HS	80 µm	
		Totaal	200 µm		
	2	EP	Monopox LG Micro Zink	40 µm	
		EP	Monopox Metalsealer	80 µm	
		PUR	Polyfinish HS	60 µm	
		Totaal	180 µm		

De hierboven vermelde systemen zijn voorbeeldsystemen. In veel gevallen wordt er gevraagd om specifieke eisen door een opdrachtgever en/of applicateur. Voor een op maat gemaakt advies kunt u zich wenden tot onze technische afdeling.

Versiedatum: 3-5-2016



All our offers, contracts, deliveries, services and all correspondence, including email, are subject to the General Terms and Conditions of Delivery from the branch organisation of the Paint Printing Ink Industry (VVFV) of 2003 which are deposited at the office of the Clerk of the District Court of Amsterdam; number and date on request. They are an integral part of all contracts that we conclude with our contractual partners for the deliveries and services we offer. Of the Uniform Sales conditions deviating purchasing conditions of the buyer will not be accepted by us. See Article 1 of the Uniform Sales conditions on [www.zandleven.com](http://www.zandleven.com)

