



# zandleven coatings

Corrosie classificatie volgens ISO 12944-5

Beschermingsduur	Systeemnr.	Type	Product	laagdikte
C4  0 - 5 jaar	1	EP	Acraton HS-U	140 µm
		PUR	Polyfinish HS	60 µm
		Totaal	200 µm	
	2	EP	Acraton HS-U	200 µm
		Totaal	200 µm	

5 - 15 jaar	1	EP	Monopox ZF Universal	80 µm
		EP	Acraton HS-U	100 µm
		PUR	Polyfinish HS	60 µm
	Totaal	240 µm		
	2	EP	Acraton HS-U	140 µm
		PUR	Polyfinish HS	100 µm
Totaal		240 µm		

> 15 jaar	1	EP	Monopox ZF Universal	80 µm
		EP	Acraton HS-U	140 µm
		PUR	Polyfinish HS	60 µm
	Totaal	280 µm		
	2	EP	Acraton HS-U	160 µm
		PUR	Polyfinish HS	120 µm
		Totaal	280 µm	
	3	EP	Monopox LG Micro Zink	40 µm
		EP	Monopox Metalsealer	120 µm
PUR		Polyfinish HS	80 µm	
Totaal		240 µm		

De hierboven vermelde systemen zijn voorbeeldsystemen. In veel gevallen wordt er gevraagd om specifieke eisen door een opdrachtgever en/of applicateur. Voor een op maat gemaakt advies kunt u zich wenden tot onze technische afdeling.

Versiedatum: 3-5-2016



All our offers, contracts, deliveries, services and all correspondence, including email, are subject to the General Terms and Conditions of Delivery from the branch organisation of the Paint Printing Ink Industry (VVFV) of 2003 which are deposited at the office of the Clerk of the District Court of Amsterdam; number and date on request. They are an integral part of all contracts that we conclude with our contractual partners for the deliveries and services we offer. Of the Uniform Sales conditions deviating purchasing conditions of the buyer will not be accepted by us. See Article 1 of the Uniform Sales conditions on [www.zandleven.com](http://www.zandleven.com)

