



# zandleven coatings

Corrosion classification according ISO 12944-5:2018, Steel substrate

Durability	System no.	Type	Product	DFT	
C3	1	AK	Zancor SF-X	80 m	
		AK	Zancor ZF-xx	40 m	
		Total		120 m	
	1 - 7 years	2	EP	Monopox Metalcoat ZL 70	80 m
			PUR	Polyfinish MU-DL	40 m
			Total		120 m


7 - 15 years	1	EP	Monopox Metalcoat ZL 70	80 m
		PUR	Polyfinish HS	80 m
		Total		160 m
	2	EP	Monopox Metalcoat ZL 70	100 m
		PUR	Polyfinish HS	60 m
		Total		160 m

15 - 25 years	1	EP	Acraton HS-U	120 m
		PUR	Polyfinish HS	80 m
		Total		200 m
	2	EP	Monopox LG Micro Zink	40 m
		EP	Monopox Metalsealer	60 m
		PUR	Polyfinish HS	60 m
		Total		160 m

> 25 years	1	EP	Monopox ZF Universal	80 m
		EP	Monopox HB coating	100 m
		PUR	Polyfinish HS	60 m
		Total		240 m
	2	EP	Acraton HS-U	160 m
		PUR	Polyfinish HS	120 m
		Total		280 m
	3	EP	Monopox LG Micro Zink	40 m
		EP	Monopox Metalsealer	80 m
		PUR	Polyfinish HS	80 m
		Total		200 m

The systems mentioned above are example systems. In many cases there is asked for specific demands by an contracting party and/or applicator. Please contact our technical department for a tailor made advice.

Validation date: 2-7-2018



All our offers, contracts, deliveries, services and all correspondence, including email, are subject to the General Terms and Conditions of Delivery from the branch organisation of the Paint Printing ink Industry (VVFV) of 2003 which are deposited at the office of the Clerk of the District Court of Amsterdam; number and date on request. They are an integral part of all contracts that we conclude with our contractual partners for the deliveries and services we offer. Of the Uniform Sales conditions deviating purchasing conditions of the buyer will not be accepted by us. See Article 1 of the Uniform Sales conditions on [www.zandleven.com](http://www.zandleven.com)

