

## zandleven coatings

## Corrosion classification according ISO 12944-5:2018, Steel substrate

Durability	System no.	Type	Product	D	FT
C4					
	1	EP	Acraton HS-U	140	m
		PUR	Polyfinish HS	60	m
1 - 7 years			Total	200	m
	2	EP	Acraton HS-U	200	m
			Total	200	m
	1	EP	Monopox ZF Universal	70	m
		EP	Monopox HB coating	70	m
		PUR	Polyfinish HS	60	m
7 - 15 years			Total	200	m
	2	EP	Acraton HS-U	140	m
		PUR	Polyfinish HS	100	m
			Total	240	m
	1	EP	Monopox ZF Universal	80	m
		EP	Acraton HS-U	100	m
		PUR	Polyfinish HS	60	m
			Total	240	m
15 - 25 years	2	EP	Acraton HS-U	160	m
		PUR	Polyfinish HS	120	m
			Total	280	m
	3	EP	Monopox LG Micro Zink	40	m
		EP	Monopox Metalsealer	80	m
		PUR	Polyfinish HS	80	m
			Total	200	





	1	EP	Acraton HS-U	100	m
		EP	Acraton HS-U	120	m
		PUR	Polyfinish HS	80	m
			Total	300	m
> 25 jaar	2	EP	Acraton HS 400	240	m
		PUR	Polyfinish HS	80	m
			Total	320	m
	3	EP	Monopox Micro Zink	40	m
		EP	Acraton HS-U	160	m
		PUR	Polyfinish HS	80	m
			Total	260	m

The systems mentioned above are example systems. In many cases there is asked for specific demands by an contracting party and/or applicator. Please contact our technical department for a tailor made advice.

Validation date: 2-7-2018



