



zandleven coatings

Corrosion classification according ISO 12944-5:2018, Steel substrate


Durability	System no.	Type	Product	DFT
C5 1 - 7 years	1	EP	Acraton HS-U	100 m
		PUR	Polyfinish HS	80 m
		Total		180 m

7 - 15 years	1	EP	Acraton HS-U	100 m
		EP	Acraton HS-U	100 m
		PUR	Polyfinish HS	60 m
		Totaal		260 m
	2	EP	Monopox Micro Zink	40 m
		EP	Monopox Metalealer	100 m
		PUR	Polyfinish HS	60 m
		Total		200 m

15 - 25 years	1	EP	Acraton HS-U	120 m
		EP	Acraton HS-U	120 m
		PUR	Polyfinish HS	80 m
		Total		320 m
	2	EP	Acraton HS 400	240 m
		PUR	Polyfinish HS	80 m
		Total		320 m
	3	EP	Monopox Micro Zink	40 m
		EP	Acraton HS-U	140 m
		PUR	Polyfinish HS	80 m
		Total		260 m

The systems mentioned above are example systems. In many cases there is asked for specific demands by an contracting party and/or applicator. Please contact our technical department for a tailor made advice.

Validation date: 2-7-2018



All our offers, contracts, deliveries, services and all correspondence, including email, are subject to the General Terms and Conditions of Delivery from the branch organisation of the Paint Printing ink Industry (VVFV) of 2003 which are deposited at the office of the Clerk of the District Court of Amsterdam; number and date on request. They are an integral part of all contracts that we conclude with our contractual partners for the deliveries and services we offer. Of the Uniform Sales conditions deviating purchasing conditions of the buyer will not be accepted by us. See Article 1 of the Uniform Sales conditions on www.zandleven.com

