




# zandleven coatings

Korrosionsschutzklassen gemäß ISO 12944-5:2018

Schutzdauer	Systemnr.	Gruppe	Produkt	Schichtdicke
<b>C5</b>	<b>Fuerverzinkter Stahl /Gemetalliseerd staal</b>			
1 - 7 Jahre	1	EP	Monopox ZF-Universal	80 m
		PUR	Polyfinish HS	80 m
			Gesamt	160 m
	2	EP	Monopox Metalsealer	80 m
		PUR	Polyfinish Ijzergimmer HB	80 m
			Gesamt	160 m
7 - 15 Jahre	1	EP	Monopox ZF-Universal	80 m
		EP	Monopox HB Coating	80 m
		PUR	Polyfinish HS	80 m
		Gesamt	240 m	
	2	EP	Monopox Metalsealer	80 m
		EP	Monopox HB Ijzergimmer	80 m
		PUR	Polyfinish HS	80 m
		Gesamt	240 m	
	15 - 25 Jahre	1	EP	Monopox ZF-Universal
EP			Acraton HS-U	160 m
PUR			Polyfinish HS	80 m
			Gesamt	320 m

Diese Daten sind nach bestem Wissen erstellt und waren zum Datum der Ausgabe korrekt. Diese Hinweise sind unverbindlich, da die Wahl der Produkte unter Umständen beim Verarbeiten von den Systemen außerhalb unserer Beurteilung liegen. Dieses Dokumentationsblatt wird bei Änderungen nicht automatisch ersetzt.

Stand: 2-7-2018



All our offers, contracts, deliveries, services and all correspondence, including email, are subject to the General Terms and Conditions of Delivery from the branch organisation of the Paint Printing ink Industry (VVFV) of 2003 which are deposited at the office of the Clerk of the District Court of Amsterdam; number and date on request. They are an integral part of all contracts that we conclude with our contractual partners for the deliveries and services we offer. Of the Uniform Sales conditions deviating purchasing conditions of the buyer will not be accepted by us. See Article 1 of the Uniform Sales conditions on [www.zandleven.com](http://www.zandleven.com)

