

zandleven coatings

Atmospheric corrosivity categories in accordance with ISO 12944:2018

Durability	Systemnr.	Туре	Product	DFT
C1 / C2				
	1	AK	Zancor SF-X	80 µm
			Total	80 µm
1 - 7 years				
	2	EP	Monopox Metalcoat ZL 70	80 µm
			Total	80 µm
	3	EP	Acraton WV-ZF	70 µm
			Total	70 µm
	4	PUR	Polyfinish DTM 50-xx	80 µm
			Total	80 µm
	5	PUR	Polyfinish DTM HS 70-xx	80 µm
			Total	80 µm

	1	AK	Zancor SF-X	60 µm
		AK	Zancor ZF-xx	40 µm
7 - 15 years			Total	100 µm
	2	EP	Monopox Metalcoat ZL 70	100 µm
			Total	100 µm
	3	EP	Acraton WV-ZF	60 µm
		AY	Acrylex AE	40 µm
			Total	100 µm
	4	EP	Acraton WV-ZF	60 µm
		PUR	Polyfinish H2O	40 µm
			Total	100 µm
	5	PA	Polyfinish Aspartic 80-75	100 µm
			Total	100 µm
	6	PUR	Polyfinish DTM HS 70-xx	100 μm
			Total	100 µm



	1	EP	Monopox Metalcoat ZL 80	120 µm
			Total	120 µm
15 - 25 years				
	2	EP	Monopox Metalcoat ZL 70	60 µm
		PUR	Polyfinish HS	60 µm
			Total	120 µm
	3	PA	Polyfinish Aspartic 80-75	120 µm
			Total	
	4	AK	Zancor SF-X	80 µm

	1	EP	Acraton HS-U	120 µm
		PUR	Polyfinish HS	60 µm
			Total	180 µm
> 25 years				
	2	EP	Monopox LG Micro Zink	40 µm
		EP	Monopox Metalsealer	60 µm
		PUR	Polyfinish HS	60 µm
			Total	160 µm

Listed coating systems are some examples of typical environments. Nevertheless, detailed coating systems can be made, based on detailed information. Please consult our technical department.

Issue date: 1-2-2024

