



zandleven coatings

Atmospheric corrosivity categories in accordance with ISO 12944:2018

Durability	Systemnr.	Type	Product	DFT
Cx	Hot dip galvanized steel /Thermal sprayed steel			

Cx (offshore)	1	EP	Monopox Metalsealer	60 µm
		EP	Acraton HS-U/Mio	120 µm
		PUR	Polyfinish HS 65-55	60 µm
			Total	240 µm

Listed coating systems are some examples of typical environments. Nevertheless, detailed coating systems can be made, based on detailed information. Please consult our technical department.

Issue date: 1-2-2024



All our offers, contracts, deliveries, services and all correspondence, including email, are subject to the General Terms and Conditions of Delivery from the branch organisation of the Paint Printing Ink Industry (VVF) of 2003 which are deposited at the office of the Clerk of the District Court of Amsterdam; number and date on request. They are an integral part of all contracts that we conclude with our contractual partners for the deliveries and services we offer. Of the Uniform Sales conditions deviating purchasing conditions of the buyer will not be accepted by us. See Article 1 of the Uniform Sales conditions on www.zandleven.com