

## zandleven coatings

Immersion corrosivity categories in accordance with ISO 12944:2018

Immersion	Systemnr.	Туре	Product	DFT
Im 1 up to Im 3	Hot dip galvanize steel /Thermal sprayed steel			
	1	EP	Monopox Metalsealer	80 µm
		EP	Acraton HS-U	165 µm
lm 1		PUR	Polyfinish HS 65-55	65 µm
fresh water			Total	310 µm
>25 years				
	2	EP	Monopox Metalsealer	80 µm
		EP	Acraton HS-U	150 µm
		EP	Acraton HS-U	150 µm
			Total	380 µm

	1	EP EP	Monopox Metalsealer Acraton HS-U	80 µm 165 µm
lm 2		PUR	Polyfinish HS 65-55	65 µm
sea or			Total	310 µm
brackish water				
>25 years	2	EP	Monopox Metalsealer	80 µm
		EP	Acraton HS-U	150 µm
		EP	Acraton HS-U	150 µm
			Total	380 µm

	1	EP	Monopox Metalsealer	80 µm
		EP	Acraton HS-U	165 µm
Im 3		PUR	Polyfinish HS 65-55	65 µm
soil			Total	310 µm
>25 years	2			
		EP	Monopox Metalsealer	80 µm
		EP	Acraton HS-U	150 µm
		EP	Acraton HS-U	150 µm
			Total	380 µm

Listed coating systems are some examples of typical environments. Nevertheless, detailed coating systems can be made, based on detailed information. Please consult our technical department.

Issue date: 1-2-2024

