



Corrosie classificatie volgens ISO 12944:2018

Beschermingsduur	Systeemnr.	Type	Product	laagdikte
C5				
1 - 7 jaren	1	EP	Acraton HS-U	120 µm
		PUR	Polyfinish HS	60 µm
			Totaal	180 µm
	2	EP	Acraton WV-ZF	70 µm
		EP	Acraton WV-HB	70 µm
		AY	Acrylex AE	40 µm
			Totaal	180 µm
	3	EP	Acraton WV-ZF	60 µm
		EP	Acraton WV-HB	60 µm
		AY	Polyfinish H2O	60 µm
			Totaal	180 µm

7 - 15 jaren	1	EP	Monopox Metalcoat ZL70	80 µm
		EP	Acraton HS-U	100 µm
		PUR	Polyfinish HS	60 µm
			Totaal	240 µm
	2	EP	Monopox Micro Zink	40 µm
		EP	<u>Monopox Metalealer</u>	<u>100 µm</u>
		PUR	Polyfinish HS	60 µm
			Totaal	200 µm
	3	EP	Monopox Premium	80 µm
		EP	<u>Monopox Premium</u>	<u>100 µm</u>
		PUR	Polyfinish HS	60 µm
			Totaal	240 µm
	4	PUR	Polyfinish MC Zink HS	80 µm
		PA	Polyfinish Apsartic 80-75	160 µm
			Totaal	240 µm



All our offers, contracts, deliveries, services and all correspondence, including email, are subject to the General Terms and Conditions of Delivery from the branch organisation of the Paint Printing Ink Industry (VVFV) of 2003 which are deposited at the office of the Clerk of the District Court of Amsterdam; number and date on request. They are an integral part of all contracts that we conclude with our contractual partners for the deliveries and services we offer. Of the Uniform Sales conditions deviating purchasing conditions of the buyer will not be accepted by us. See Article 1 of the Uniform Sales conditions on www.zandleven.com

15 - 25 jaren	1	EP	Acraton HS-U	120 µm
		EP	Acraton HS-U	120 µm
		PUR	Polyfinish HS	60 µm
			Totaal	300 µm
	2	EP	Acraton HS 400	240 µm
		PUR	Polyfinish HS	80 µm
			Totaal	320 µm
	3	EP	Monopox Micro Zink	40 µm
		EP	Acraton HS-U	140 µm
		PUR	Polyfinish HS	80 µm
			Totaal	260 µm
	4	EP	Monopox Metalcoat ZL70	70 µm
		EP	Acraton HS-U	170 µm
		PUR	Polyfinish HS 65-55	55 µm
			Totaal	295 µm
	5	PUR	Polyfinish MC Zink HS	80 µm
		EP	Monopox Metalsealer	100 µm
		PUR	Polyfinish HS	60 µm
			Totaal	240 µm

>25 jaren	1	SI	Zinksilicaat ZL400-55	60 µm
		EP	Monopox Metalsealer	80 µm
		EP	Monopox HB coating	100 µm
		PUR	Polyfinish HS	60 µm
			Totaal	320 µm

De hierboven vermelde systemen zijn voorbeeldsystemen. In veel gevallen wordt er gevraagd om specifieke eisen door een opdrachtgever en/of applicateur. Voor een op maat gemaakt advies kunt u zich wenden tot onze technische afdeling.

Versiedatum: 1-2-2024



All our offers, contracts, deliveries, services and all correspondence, including email, are subject to the General Terms and Conditions of Delivery from the branch organisation of the Paint Printing Ink Industry (VVFV) of 2003 which are deposited at the office of the Clerk of the District Court of Amsterdam; number and date on request. They are an integral part of all contracts that we conclude with our contractual partners for the deliveries and services we offer. Of the Uniform Sales conditions deviating purchasing conditions of the buyer will not be accepted by us. See Article 1 of the Uniform Sales conditions on www.zandleven.com