



Corrosie classificatie volgens ISO 12944:2018

Immersie	Systeemnr.	Type	Product	laagdikte
Im 1 t/m Im 4				
Im 1 zoet water 15 – 25 jaren	1	EP	Monopox SF-HB	80 µm
		EP	Acraton HS-U	150 µm
		EP	Acraton HS-U	150 µm
			Totaal	380 µm
	2	EP	Monopox Micro Zink	40 µm
		EP	Monopox Metalsealer	80 µm
		EP	Acraton HS-U/MIO	120 µm
		EP	Acraton HS-U/MIO	120 µm
			Totaal	360 µm
	3	EP	Acraton HS-U	150 µm
		EP	Acraton HS-U	150 µm
		PUR	Polyfinish HS 65-55	90 µm
			Totaal	390 µm

Im 2 zeewater of brakwater 15 – 25 jaren	1	EP	Monopox SF-HB	80 µm
		EP	Acraton HS-U	150 µm
		EP	Acraton HS-U	150 µm
			Totaal	380 µm
	2	EP	Monopox Micro Zink	40 µm
		EP	Monopox Metalsealer	80 µm
		EP	Acraton HS-U/MIO	120 µm
		EP	Acraton HS-U/MIO	120 µm
			Totaal	360 µm
	3	EP	Acraton HS-U	150 µm
		EP	Acraton HS-U	150 µm
		PUR	Polyfinish HS 65-55	90 µm
			Totaal	390 µm



All our offers, contracts, deliveries, services and all correspondence, including email, are subject to the General Terms and Conditions of Delivery from the branch organisation of the Paint Printing Ink Industry (VVF) of 2003 which are deposited at the office of the Clerk of the District Court of Amsterdam; number and date on request. They are an integral part of all contracts that we conclude with our contractual partners for the deliveries and services we offer. Of the Uniform Sales conditions deviating purchasing conditions of the buyer will not be accepted by us. See Article 1 of the Uniform Sales conditions on www.zandleven.com

Im 3 ondergronds 15 – 25 jaren	1	EP	Acraton HS 400	200 µm
		EP	Acraton HS 400	200 µm
			Totaal	400 µm
	2	EP	Zandguard Novacure HR	80 µm
		EP	Acraton CRT-HS Coating	150 µm
		EP	Acraton CRT-HS Coating	150 µm
			Totaal	380 µm
	3	EP	Monopox SF-HB	80 µm
		EPGF	Acraton HS Glasscoat	150 µm
		EPGF	Acraton HS Glasscoat	150 µm
			Totaal	380 µm

Im 4 Zeewater of Brakwater + KB 15 – 25 jaren	1	EP	Monopox SF-HB	80 µm
		EP	Acraton HS-U	150 µm
		EP	Acraton HS-U	150 µm
			Totaal	380 µm
	2	EP	Monopox Micro Zink	40 µm
		EP	Monopox Metalsealer	80 µm
		EP	Acraton HS-U/MIO	120 µm
		EP	Acraton HS-U/MIO	120 µm
			Totaal	360 µm

De hierboven vermelde systemen zijn voorbeeldsystemen. In veel gevallen wordt er gevraagd om specifieke eisen door een opdrachtgever en/of applicateur. Voor een op maat gemaakt advies kunt u zich wenden tot onze technische afdeling.

Versiedatum: 1-2-2024



All our offers, contracts, deliveries, services and all correspondence, including email, are subject to the General Terms and Conditions of Delivery from the branch organisation of the Paint Printing Ink Industry (VVF) of 2003 which are deposited at the office of the Clerk of the District Court of Amsterdam; number and date on request. They are an integral part of all contracts that we conclude with our contractual partners for the deliveries and services we offer. Of the Uniform Sales conditions deviating purchasing conditions of the buyer will not be accepted by us. See Article 1 of the Uniform Sales conditions on www.zandleven.com