





**TRANSOCEAN
COATINGS**

transocean coatings



DSB stadion Alkmaar



IJSbaan De Uithof Den Haag



Sportcentrum Olympiakwartier, Almere Poort



ADO stadion Den Haag



IJSbaan Hoor



Euroborg stadion Groningen

proposed coating systems

project	Pre-treatment	primer	layers	topcoat
DSB Stadion	Sa 2 1/2	94.67 Transoxy Masterbond 120 µm	94.67 Transoxy Masterbond 120 µm	93.47 Transurethane Finish HS 60 µm
Olympiakwartier	Sa 2 1/2	91.79 Transozinc RZ Epoxy Primer 60 µm	92.19 Transoxy Inter-mediate 60 µm	92.19 Transoxy Inter-mediate 60 µm
IJSbaan Hoor	Sa 2 1/2	92.16 Transoxy Masterbond 100 µm	92.16 Transoxy Masterbond 100 µm	93.47 Transurethane Finish HS 75 µm
Uithof Den Haag	Sa 2 1/2	91.61 Transoxy ZP Primer 80 µm	92.19 Transoxy Inter-mediate 80 µm	93.47 Transurethane Finish HS 70 µm
ADO stadion	Sa 2 1/2	91.79 Transozinc RZ Epoxy Primer 50 µm	92.19 Transoxy Inter-mediate 100 µm	93.47 Transurethane Finish HS 60 µm
Euroborg	Sa 2 1/2	94.67 Transoxy Masterbond 150 µm		93.47 Transurethane Finish HS 75 µm

All technical data sheets and other information about coating application are available at our website: www.transoceancoatings.com



Ganzlin

