



zandleven coatings

Thermaguard® CUI 300

siloxane

Thermaguard CUI 300 is a single pack, inert multi polymeric matrix, high build primer, designed with special pigments and additives, obtaining a coating with high temperature resistance up to 300°C, boiling water resistant and suitable for cyclic thermal conditions.

- Prevents corrosion under insulation (CUI), on carbon steel and stainless steel substrate
- Drying and hardening will take place at room temperature
- Damage due to transportation will be reduced
- To apply on hot substrate, up to 150°C
- Application without shutdown
- Application on mechanically pre-treated substrates

Specific properties

- As anti corrosion primer, on insulated as well on non-insulated generic processing, pipework, vessels, tanks and as primer for Thermaguard TC1200 topcoat.
- Thermaguard CUI 300 meets the NACE SP0198-2017 requirements
- High solid content and low VOC value
- Exceptional resistance to thermal cycling high temperature up 300°C
- Prevents stainless steel cracking, due to chloride exposure
- Operating range within -196°C to 300°C
- Recoatable after ageing, in accordance with application instructions

Product information at 20°C

Finish	Matt
Color	RAL 3009 and RAL 7035
Mass density	approx. 1.90 kg/L
Solids content by volume	approx. 72 volume %
VOC	approx. 225 gr./L (volatile organic compound)
Recommended film thickness	brush application: 3 layers of 80 micron DFT Spray application: 2 layers of 120 micron DFT Above mentioned film thickness shouldn't be exceeded by more than 50%.
Theoretical spreading rate	At 80 µm d.f.t. 9.0 m²/L At 120 µm d.f.t. 6.0 m²/L
Practical spreading rate	Depending on several factors like shape of object, profile of surface, method of application, application circumstances and experience. A few guiding principles are: Brush/roller 85-90% of the theoretical spreading rate Spraying 50-70% of the theoretical spreading rate
Flashpoint ISO 1523	Paint >61°C Thinner BB 55 27°C Thinner FF 55 41°C
Dry temperature resistance	-196°C up to +300°C
Shelf life	Material should be stored in a dry, shaded environment away from heat & ignition sources. Do not allow material to freeze. Shelf life is minimum 12 months at 23°C.



Drying times

For d.f.t. up to 75 µm

Dust dry

Manageable

Recoatable:

Minimum interval

Maximum interval

Application of the isolation

35°C	23°C	10°C
15 minutes	30 minutes	60 minutes
16 hours	24 hours	30 hours
1 hour	2 hours	4 hours
Unlimited, provided that the surface is clean and dry.		
Film thickness, ventilation, temperature and relative humidity are of great influence on the drying times.		
After 48 hours after the last layer has dried.		

Application instructions

Application conditions

During the application and the hardening the temperature should be above 5°C.

The surface should remain dry and the temperature of the surface should at least be 3°C above dew point.

During application and hardening in closed or small spaces, it is necessary to refresh the air continually to remove the solvent vapours, this because of drying, health and safety.

Usage information

Type of thinner

Recommended thinner (depending on application and equipment)

Nozzle orifice

Nozzle pressure

Maximum attainable d.f.t.

Cleaning of tools

Airless-spray	Airspray	Brush/roller
BB 55 / FF 55	BB 55	BB 55
0 – 5 vol. %	5 – 10 vol. %	0 – 5 vol. %
0.38 – 0.53 mm 0.015 – 0.021 inch	1.8 – 2.2 mm	
160 – 200 bar	2 – 3 bar	
150 µm	120 µm	80 µm
Thinner BB 55		

Surface conditions

Steel

New steel:

Abrasive blast clean to Sa 2½ (ISO 8501-1:2007) or SSPC-SP10. The resulting surface profile should be: Rz 30 – 50 µm.

Stainless steel

New stainless steel:

Abrasive sweep clean using non-metallic & chloride free abrasive. The resulting surface profile Rz should be: 30 – 50 µm.

Repair and maintenance

Clean the surface thoroughly with a suitable cleaning preparation or by steam cleaning.

Remove salts and other water soluble impurity by spraying with clean tap-water under high pressure.

Remove rust a.o. by (water)blasting Sa 2½ or derust mechanical until St. 2-3, in accordance with ISO 8501-1:2007.

Apply the advised paint system on a clean surface.

- Mechanical or hand derusting gives less quality than (water)blasting
- and will result in less protection of the applied paint system.

Application substrate temperature

Thinner BB55, from 10°C up to 60°C

Thinner FF55, from 60°C up to 150°C



zandleven coatings

Thermaguard® CUI 300

siloxane

Ventilation precaution

Minimum required quantity of air to comply with:

	IOELV(EU)	10 % LEL
Thermaguard CUI 300	1102 m³/L	46 m³/L
Thinner BB 55	3935 m³/L	165 m³/L
Thinner FF 55	1750 m³/L	163 m³/L

IOELV = Indicative Occupational Exposure Limit Values

LEL = Lower Explosion Limit

Also consult the security information sheets

Additional and applicable information (www.zandleven.com)

- General guidelines
- Material Safety Data Sheet
- information curing agents en thinners
- Color surcharge
- General terms and conditions of delivery



These data have been drawn up to the best of our knowledge and were correct at the date of issue. However we cannot accept full responsibility, because de choice of products and circumstances during elaboration of the systems fall outside our judgement. This documentation sheet will not automatically be replaced in case of modification.
The English language text is a translation. In case of doubt the Dutch language original text has to be consulted as the authoritative text.