



Atmosphärische Korrosivitätskategorien gemäß ISO 12944:2018

Schutzdauern	System Nr.	Typ	Produkt	Schicht Dicke
C1 / C2				
1 - 7 Jahre	1	AK	Zancor SF-X	80 µm
			Gesamt Schicht Dicke	80 µm
	2	EP	Monopox Metalcoat ZL 70	80 µm
			Gesamt Schicht Dicke	80 µm
	3	EP	Acraton WV-ZF	70 µm
			Gesamt Schicht Dicke	70 µm
	4	PUR	Polyfinish DTM 50-xx	80 µm
			Gesamt Schicht Dicke	80 µm
	5	PUR	Polyfinish DTM HS 70-xx	80 µm
			Gesamt Schicht Dicke	80 µm

7 - 15 Jahre	1	AK	Zancor SF-X	60 µm
		AK	Zancor ZF-xx	40 µm
			Gesamt Schicht Dicke	100 µm
	2	EP	Monopox Metalcoat ZL 70	100 µm
			Gesamt Schicht Dicke	100 µm
	3	EP	Acraton WV-ZF	60 µm
		AY	Acrylex AE	40 µm
			Gesamt Schicht Dicke	100 µm
	4	EP	Acraton WV-ZF	60 µm
		PUR	Polyfinish H2O	40 µm
			Gesamt Schicht Dicke	100 µm
	5	PA	Polyfinish Aspartic 80-75	100 µm
			Gesamt Schicht Dicke	100 µm
	6	PUR	Polyfinish DTM HS 70-xx	100 µm
			Gesamt Schicht Dicke	100 µm



All our offers, contracts, deliveries, services and all correspondence, including email, are subject to the General Terms and Conditions of Delivery from the branch organisation of the Paint Printing Ink Industry (VVF) of 2003 which are deposited at the office of the Clerk of the District Court of Amsterdam; number and date on request. They are an integral part of all contracts that we conclude with our contractual partners for the deliveries and services we offer. Of the Uniform Sales conditions deviating purchasing conditions of the buyer will not be accepted by us. See Article 1 of the Uniform Sales conditions on www.zandleven.com

15 - 25 Jahre	1	EP	Monopox Metalcoat ZL 80	120 µm
			Gesamt Schicht Dicke	120 µm
	2	EP	Monopox Metalcoat ZL 70	60 µm
		PUR	Polyfinish HS	60 µm
			Gesamt Schicht Dicke	120 µm
	3	PA	Polyfinish Aspartic 80-75	120 µm
			Gesamt Schicht Dicke	
	4	AK	Zancor SF-X	80 µm

> 25 Jahre	1	EP	Acraton HS-U	120 µm
		PUR	Polyfinish HS	60 µm
			Gesamt Schicht Dicke	180 µm
	2	EP	Monopox LG Micro Zink	40 µm
		EP	Monopox Metalsealer	60 µm
		PUR	Polyfinish HS	60 µm
			Gesamte Schicht Dicke	160 µm

Bei den oben aufgeführten Systemen handelt es sich um Beispielsystemen. In vielen Fällen werden von einem Kunden und/oder Anwender spezifische Anforderungen gestellt. Für eine individuelle Beratung wenden Sie sich bitte an unsere technische Abteilung

Stand: 1-2-2024



All our offers, contracts, deliveries, services and all correspondence, including email, are subject to the General Terms and Conditions of Delivery from the branch organisation of the Paint Printing Ink Industry (VVF) of 2003 which are deposited at the office of the Clerk of the District Court of Amsterdam; number and date on request. They are an integral part of all contracts that we conclude with our contractual partners for the deliveries and services we offer. Of the Uniform Sales conditions deviating purchasing conditions of the buyer will not be accepted by us. See Article 1 of the Uniform Sales conditions on www.zandleven.com