



Atmosphärische Korrosivitätskategorien gemäß ISO 12944:2018

Schutzdauern	System Nr.	Typ	Produkt	Schicht Dicke
C5				
1 - 7 Jahre	1	EP	Acraton HS-U	120 µm
		PUR	Polyfinish HS	60 µm
			Gesamt Schicht Dicke	180 µm
	2	EP	Acraton WV-ZF	70 µm
		EP	Acraton WV-HB	70 µm
		AY	Acrylex AE	40 µm
			Gesamt Schicht Dicke	180 µm
	3	EP	Acraton WV-ZF	60 µm
		EP	Acraton WV-HB	60 µm
		AY	Polyfinish H2O	60 µm
			Gesamt Schicht Dicke	180 µm

7 - 15 Jahre	1	EP	Monopox Metalcoat ZL70	80 µm
		EP	Acraton HS-U	100 µm
		PUR	Polyfinish HS	60 µm
			Gesamt Schicht Dicke	240 µm
	2	EP	Monopox Micro Zink	40 µm
		EP	Monopox Metalealer	100 µm
		PUR	Polyfinish HS	60 µm
			Gesamt Schicht Dicke	200 µm
	3	EP	Monopox Premium	80 µm
		EP	Monopox Premium	100 µm
		PUR	Polyfinish HS	60 µm
			Gesamt Schicht Dicke	240 µm
	4	PUR	Polyfinish MC Zink HS	80 µm
		PA	Polyfinish Apsartic 80-75	160 µm
			Gesamt Schicht Dicke	240 µm



All our offers, contracts, deliveries, services and all correspondence, including email, are subject to the General Terms and Conditions of Delivery from the branch organisation of the Paint Printing Ink Industry (VVFV) of 2003 which are deposited at the office of the Clerk of the District Court of Amsterdam; number and date on request. They are an integral part of all contracts that we conclude with our contractual partners for the deliveries and services we offer. Of the Uniform Sales conditions deviating purchasing conditions of the buyer will not be accepted by us. See Article 1 of the Uniform Sales conditions on www.zandleven.com

15 - 25 Jahre	1	EP	Acraton HS-U	120 µm
		EP	Acraton HS-U	120 µm
		PUR	Polyfinish HS	60 µm
			Gesamt Schicht Dicke	300 µm
	2	EP	Acraton HS 400	240 µm
		PUR	Polyfinish HS	80 µm
			Gesamt Schicht Dicke	320 µm
	3	EP	Monopox Micro Zink	40 µm
		EP	Acraton HS-U	140 µm
		PUR	Polyfinish HS	80 µm
			Gesamt Schicht Dicke	260 µm
	4	EP	Monopox Metalcoat ZL70	70 µm
		EP	Acraton HS-U	170 µm
		PUR	Polyfinish HS 65-55	55 µm
			Gesamt Schicht Dicke	295 µm
	5	PUR	Polyfinish MC Zink HS	80 µm
		EP	Monopox Metalsealer	100 µm
		PUR	Polyfinish HS	60 µm
			Gesamt Schicht Dicke	240 µm

>25 Jahre	1	SI	Zinksilicaat ZL400-55	60 µm
		EP	Monopox Metalsealer	80 µm
		EP	Monopox HB coating	100 µm
		PUR	Polyfinish HS	60 µm
			Gesamt Schicht Dicke	320 µm

Bei den oben aufgeführten Systemen handelt es sich um Beispielsystemen. In vielen Fällen werden von einem Kunden und/oder Anwender spezifische Anforderungen gestellt. Für eine individuelle Beratung wenden Sie sich bitte an unsere technische Abteilung

Stand: 1-2-2024



All our offers, contracts, deliveries, services and all correspondence, including email, are subject to the General Terms and Conditions of Delivery from the branch organisation of the Paint Printing Ink Industry (VVFV) of 2003 which are deposited at the office of the Clerk of the District Court of Amsterdam; number and date on request. They are an integral part of all contracts that we conclude with our contractual partners for the deliveries and services we offer. Of the Uniform Sales conditions deviating purchasing conditions of the buyer will not be accepted by us. See Article 1 of the Uniform Sales conditions on www.zandleven.com