



Atmosphärische Korrosivitätskategorien gemäß ISO 12944:2018

Schutzdauern	System Nr.	Typ	Produkt	Schicht Dicke
C5	Feuer Verzinkter Stahl /Thermisch gespritzter Stahl			
1 - 7 Jahre	1	EP	Monopox ZF-Universal	60 µm
		PUR	Polyfinish HS	60 µm
			Gesamt Schicht Dicke	120 µm
	2	EP	Monopox Metalsealer	60 µm
		PUR	Polyfinish IJzerlgimmer HB	60 µm
			Gesamt Schicht Dicke	120 µm
	3	EP	Monopox Metalsealer	60 µm
		PUR	Polyfinish HS	60 µm
			Gesamt Schicht Dicke	120 µm

7 - 15 Jahre	1	EP	Monopox ZF-Universal	80 µm
		PUR	Polyfinish HS	80 µm
			Gesamt Schicht Dicke	160 µm
	2	EP	Monopox Metalsealer	80 µm
		PUR	Polyfinish HS	80 µm
			Gesamt Schicht Dicke	160 µm

15 - 25 Jahre	1	EP	Monopox ZF-Universal	70 µm
		EP	Monopox HB coating	70 µm
		PUR	Polyfinish HS	60 µm
			Gesamt Schicht Dicke	200 µm
	2	EP	Monopox Metalsealer	70 µm
		EP	Monopox HB coating	70 µm
		PUR	Polyfinish HS	60 µm
			Gesamt Schicht Dicke	200 µm



All our offers, contracts, deliveries, services and all correspondence, including email, are subject to the General Terms and Conditions of Delivery from the branch organisation of the Paint Printing Ink Industry (VVF) of 2003 which are deposited at the office of the Clerk of the District Court of Amsterdam; number and date on request. They are an integral part of all contracts that we conclude with our contractual partners for the deliveries and services we offer. Of the Uniform Sales conditions deviating purchasing conditions of the buyer will not be accepted by us. See Article 1 of the Uniform Sales conditions on www.zandleven.com

>25 Jahre	1	EP	Monopox Metalsealer	80 µm
		EP	Monopox HB coating	100 µm
		PUR	Polyfinish HS	60 µm
				Gesamt Schicht Dicke 240 µm
	2	EP	Monopox Metalsealer	110 µm
		PA	Polyfinis Aspartic	200 µm
				Gesamt Schicht Dicke 310 µm

Bei den oben aufgeführten Systemen handelt es sich um Beispielsystemen. In vielen Fällen werden von einem Kunden und/oder Anwender spezifische Anforderungen gestellt. Für eine individuelle Beratung wenden Sie sich bitte an unsere technische Abteilung

Stand: 1-2-2024



All our offers, contracts, deliveries, services and all correspondence, including email, are subject to the General Terms and Conditions of Delivery from the branch organisation of the Paint Printing ink Industry (VVF) of 2003 which are deposited at the office of the Clerk of the District Court of Amsterdam; number and date on request. They are an integral part of all contracts that we conclude with our contractual partners for the deliveries and services we offer. Of the Uniform Sales conditions deviating purchasing conditions of the buyer will not be accepted by us. See Article 1 of the Uniform Sales conditions on www.zandleven.com